

TECHNICAL DATA

| <u>DESCRIPTION</u> | <u>TEST STANDARD</u> | <u>RESULT</u> |
|--|---|---------------|
| Color Fastness to Artificial Weathering | BS EN ISO 105:B04 - max 8 | 7 - 8 |
| Color Fastness to Rubbing | EN ISO 105-X12 | |
| | Dry Rubbing | Pass |
| | Wet Rubbing | Pass |
| Color Fastness to Chlorinated Pool Water | BS EN ISO 105-E03 - max 5 | Pass |
| Color Fastness to Sea Water | BS EN ISO 105-E02 - max 5 | Pass |
| Soil Release | AATCC 130 | 5 |
| Dimensional Stability to washing | EN ISO 6330 | |
| | - Length | <-1.0% |
| | - Width | <-1.0% |
| Weatherability | ASTM G53 - 96 - American Standard (hours) | 1,500 |
| Pilling Resistance | EN ISO - 12945 - 2 - max 5 after 2,000 rubs | 4 - 5 |
| Seam Slippage | prEN ISO 13936 - 2 | 5 |
| Tear Strength | EN ISO 13937-3 | Pass |
| Tensile Strength | EN ISO 13934-1 | Pass |
| Water Repellency | AATCC Test Method 22 - 2005 - max 100 | 80 |
| Flammability | BS EN 1021-1, 2006 - Cigarette | Pass |
| Anti Mildew | AATC 147 : 2011 & 30 : 2004 | Pass |
| Care Instruction |      | |

Stock may vary from sample in color & texture.

In spite of excellent properties, Olefin yarn has a certain level of durability (depends on climate and proper use of fabric)



Produced by

